

ULINE S-574
3M INDUSTRIAL
STRAPPING TAPE

1-800-295-5510
uline.com

SPECIFICATIONS

APPLICATION TECHNIQUES

Application of the S-574 is most easily accomplished at room temperature. At colder temperatures, approaching 32°F (0°C), the adhesive becomes firmer. Once applied, S-574 performs well throughout the normal temperature ranges typically encountered by packaged products in shipping and storage environments.

CONSTRUCTION

Backing	3M Scotchpro™ Film
Adhesive	Pressure-sensitive rubber resin
Reinforcement	Glass yarn
Backing Color	Clear

SHELF LIFE:

- To obtain best performance, store in a clean, dry place. Temperature of 40-80°F (4-26°C) and 40-50% relative humidity are recommended.

PHYSICAL PROPERTY	SPECIFICATIONS	ASTM TEST METHOD
Adhesion to Steel	40 oz./in. width (43 N/100 mm)	D-3330
Tensile Strength	300 lbs./in. width (5250 N/100 mm)	D-3759
Elongation at Break	3%	D-3759
Total Tape Thickness	6.0 mil (0.15 mm)	D-3652