

PRODUCT SPECIFICATIONS

FILM PROPERTIES	UNITS		TYPICAL VALUES
Thickness	microns mils		75 3.0
Yield	g / m ² in ² / lb.		69.81 10071
Tensile Strength	MD	lbs / sq. in. N / sq. cm	5500 3800
	TD	lbs / sq. in. N / sq. cm	4800 3300
Elongation	MD	%	540
	TD	%	580
Puncture Pointed Probe	lbs.		2.9
	N		13
Oxygen Transmission 24 hrs / 23°C Dry	cc / sq. m		63
	cc / 100 sq. in.		4.1
Moisture Vapor Transmission 24 hrs / 37.8°C @ 90% R.H.	g / sq. m		4.8
	g / 100 sq. in.		0.31

**NOTE: Compatible with H-1075 Vacuum Sealer.****IMPORTANT! This data is offered for information purposes and does not represent any type of guarantee or warranty of performance.**